

TECHNICAL DATA SHEET

LIVING LINE: PRESTIGE L HYDRO

PRODUCT DOCUMENTATION



EN 14041:2004/AC:2006

PHYSICAL AND CHEMICAL CHARACTERISTICS	STANDARD REFERENCE	VALUE CLASSIFICATION
Product type	prEN 13329:2023	Laminate floor coverings
Layers		1) Overlay 2) Decorative paper 3) HDF panel 4) Backing paper
Production system		DPL
Substrate		HDF
Density	EN 323:1993	880 Kg./m ³ ± 3%
Element dimension		2052x2220x(8 ± 0,5) mm
Dimension changes	prEN 13329:2023	In accordance with tolerance table 1
Classification	prEN 13329:2023	 En 13329-23 En 13329-32
Class of use (indoor use)	prEN 13329:2023 – EN ISO 10874:2012/A1:2020	HEAVY DOMESTIC GENERAL COMMERCIAL
Abrasion resistance	prEN 13329:2023 – EN ISO 10874:2012/A1:2020	AC4
Impact resistance	prEN 13329:2023	Small ball: ≥ 35 mm Big ball: ≥ 600 mm
Resistance to scratching	EN 438-2:2005 PAR. 25	Minimum Rating 3

Rev. 01 - 05/04/2024







TECHNICAL DATA SHEET

LIVING LINE: PRESTIGE L HYDRO

PRODUCT
DOCUMENTATION

EN 14041:2004/AC:2006



PHYSICAL AND CHEMICAL CHARACTERISTICS	STANDARD REFERENCE	VALUE CLASSIFICATION
Resistance to staining	EN 438-2:2005 PAR. 26	Group 1 Rating 5 Group 2 Rating 5 Group 3 Rating 4
Colour fastness	EN ISO 4892-2:2013/A1:2021	Grey scale ≥ 4
Effect of a furniture leg "Type O"	prEN 13329:2023 – EN ISO 16581:2019	No damage
Effect of a castor chair "Type W"	prEN 13329:2023 – EN ISO 4198:2021	No damage (15.000 cycles)
Joint		 
Locking Strength	prEN 13329:2023 – EN ISO 24334:2019	Length: ≥ 2 kN/m Width: ≥ 2 kN/m
Bevel		Present on the 4 sides 
Edge Impregnation "Hydro"		YES
Water Protection Protection against the penetration of standing water on the edges	ISO 4760:2022	
Thickness swelling	prEN 13329:2023 – ISO 24336:2005	≤ 13 %
Static indentation / Residual Indentation	prEN 13329:2023 – EN ISO 24343-1:2012	$\leq 0,01$ mm

TECHNICAL DATA SHEET

LIVING LINE: PRESTIGE L HYDRO

PRODUCT
DOCUMENTATION

EN 14041:2004/AC:2006

PHYSICAL AND CHEMICAL CHARACTERISTICS	STANDARD REFERENCE	VALUE CLASSIFICATION
Surface soundness	prEN 13329:2023 - APPENDICE B	$\geq 1,25 \text{ N/mm}^2$
Forest Certification "CoC"	PEFC ST 2002:2020	PEFC Certified Certificate Number: DNVSE-PEFC-COC-168
"CAM" Conformity (minimum environmental criteria)	Italian decree 23 June 2022	YES 
Emission of volatile organic compounds (VOC) after 28 days Classification	EN ISO 16000-9:2006 ISO 16000-6:2011 French decree No. 321/2011	
Reference Declaration of Performance (DOP) Download: http://www.skema.eu/dop		DOP: LA-001
Reaction to fire	EN 14041:2004/AC:2006 – EN 13501-01:2018	Cfl -s1 ⁽¹⁾
Formaldehyde	EN 14041:2004/AC:2006 – EN 717-1:2004	$\leq 0,05 \text{ ppm}$ (CLASS E1 $\leq 0.1 \text{ ppm}$)
Slip resistance	EN 14041:2004/AC:2006 – EN 13893:2002	CLASS DS
Slip resistance Antislip inclined Plane	EN 16165:2021-12 (ex DIN 51130:2004)	R9
Electrical behaviour (propensity to accumulation of static electricity)	EN 14041:2004/AC:2006 – EN 1815:2016	Antistatic


Rev. 01 - 05/04/2024

TECHNICAL DATA SHEET

LIVING LINE: PRESTIGE L HYDRO

PRODUCT
DOCUMENTATION

EN 14041:2004/AC:2006

PHYSICAL AND CHEMICAL CHARACTERISTICS	STANDARD REFERENCE	VALUE CLASSIFICATION
Thermal conductivity	EN 14041:2004/AC:2006 – EN 12667:2001 EN 10456 :2007	λ media = 0,14 W/(m·K) ^(*2)
Thermal resistance	EN 12667:2001	R < 0,07 m ² ·K/W ^(*2)
Suitable for underfloor heating	T _{max} = max temperature of the floor surface	YES ^(*3) T _{max} ≤ 27°C 
Suitable for underfloor cooling		YES ^(*4)
Manufacture		Made in EU
Warranty Extension		YES (for details, consult the specific document with the warranty conditions)

NOTES AND WARNINGS:

(*1) laying on non-combustible building elements by the interposition of mattresses provided by Skema following the indications specified in the technical and / or sale documentation and / or in the instructions contained in the packages.

(*2) the value of conductivity and thermal resistance indicated is referring only to the laminate flooring and does not include that one of mattress or mattresses applied. For this information, please contact Skema Technical dept.

(*3) for the installation of the product with floor heating, follow the instructions given in specific documentation and / or contained in the packages.

Laminate floors can be installed on a low thickness hot water system (in direct contact with the floor) with the certainty that the support surface is suitable, i.e. flat and solid as indicated in the installation instructions and with minimal continuity gaps to avoid compromising the longevity of the joints of the slats with the “springing” of the floor. The heat distribution must be uniform over the entire surface of the floor.

(*4) for the installation of the product with floor cooling, follow the instructions given in specific documentation and / or contained in the packages.

it is necessary to ensure that the temperature on the floor does not drop to the dew point, causing the unwanted formation of condensation. In the presence of high environmental humidity, typically in summer, this safety is achieved with careful control of temperatures in the field and possibly with a dehumidification system. Follow the cooling system manufacturer’s instructions and local or European technical standards.

Note: Specifications are subject to change without notice.

Rev. 01 - 05/04/2024