

Technical Data Sheet



HydroClick





















Class 33 according to DIN EN 13329

Version: 4/2024


Profile:

megaloc
aqua protect

Core board: Classenboard HDF
Dimensions: 1285 x 192 x 7+2 mm
Quantity / Weight per box (PU): 10 pieces = 2.467 m² / approx. 16,5 kg
Quantity / Weight per pallet: 40 PU = 98.68 m² / approx. 670 kg

Characteristics	Test Method	Requirements
General Requirements		
Geometrical characteristics	EN 17539	Length: ± 0.5 mm Width: ± 0.1 mm
Thickness	EN 17539	± 0.5 mm
Squareness	EN 17539	max. ≤ 0.20 mm
Straightness	EN 17539	max. ≤ 0.30 mm/m
Flatness of the elements	EN 17539	Width: concave ≤ 0.15%, convex ≤ 0.20 % Length: concave ≤ 0.50 %, convex ≤ 1.00 %
Openings	EN 17539	∅ ≤ 0.15 mm max. ≤ 0.20 mm
Height difference	EN 17539	∅ ≤ 0.10 mm max. ≤ 0.15 mm
Residual indentation 	EN ISO 24343-1	≤ 0.05 mm
Light fastness 	EN ISO 4892-2	grey scale level ≥ 4
Classification Requirements		
Wear resistance 	ISO 24338 method A	≥ 6000 cycles (AC5)
Impact resistance 	EN 17368 EN 13329 Annex C	small - diameter ball ≥ 70 mm large - diameter ball ≥ 750 mm
Castor chair resistance 	ISO 4918	no damage with type W after 20 000 cycles
Thickness swelling 	ISO 24336	≤ 15 %
Locking strength 	ISO 24334	F _{0.2} ≥ 1.0 kN/m F _{50.2} ≥ 2.0 kN/m
Movement of a furniture leg 	EN ISO 16581	no damage with type 0
Resistance to staining 	EN 438-2	5 (group 1 and 2), 4 (group 3)
Surface soundness	EN 13329	≥ 1.25 N/mm ²
Essential Characteristics		
Reaction to fire* 	EN 13501-1	C _{fl} - s1
Slip resistance* 	EN 13893	DS
Electrostatic behavior* 	EN 1815	≤ 2 kV
Formaldehyde* 	EN 16516	E1
Thermal conductivity* 	EN 12667	≥ 0.075 W/mK
Thermal resistance* 	EN 12667	R ≤ 0.12 (m ² K)/W
Additional requirements		
VOC Emissions	  www.blauer-engel.de/uz176 • low emissions and pollutants • wood from sustainable forestry • no adverse impact on health in the living environment	 
Sustainability		
Topical moisture resistance-surface swell	ISO 4760	- Qualitative recovery swell rating final average < 3 - Recovery swell final average ≤ 0.3 mm swelling
Topical moisture resistance-water tightness of the joints	ISO 4760	No water leakage through the joints after 100 h water exposure

We guarantee consistency of our decor colours under artificial light of type D50 (CIE D50, ANSI PH 2.30, ISO 3664) and D65 (CIE D65).

* basic attributes concerning health, safety and energy saving acc. to  EN 14041

Our technical data sheets are constantly updated and adapted to the state of the art.

This edition replaces all previous versions and is valid at the time of writing.

This document is valid without signature.